

**Thermax<sup>®</sup> MOULDED PARTS**

**Technical specification**



	Product	S	HR	HD	H
Classification temperature	°C	1050	1050	1150	1200
Available densities	kg/m <sup>3</sup>	400 – 700	500 – 700	900 – 1200	400 – 600
Following values valid at		500 kg/m <sup>3</sup>	600 kg/m <sup>3</sup>	1200 kg/m <sup>3</sup>	600 kg/m <sup>3</sup>
Thermal conductivity	W/mK				
	200 °C	0.17	0.17	0.31	0.11
	400 °C	0.18	0.18	0.32	0.13
	600 °C	0.20	0.19	0.33	0.14
	800 °C	0.22	0.20	0.34	0.15
	1000 °C	0.25	0.22	0.36	0.17
Cold compressive strength	N/mm <sup>2</sup>	2.0	1.8	9.0	1.8
Modulus of rupture	N/mm <sup>2</sup>	0.9	0.9	6.0	0.9
Heat shrinkage					
at 1050 °C / 12 h	%	< 2.0	< 2.0	–	–
at 1200 °C / 12 h	%	–	–	< 2.0	< 2.0
Colour		golden	golden	golden	grey

A patented process permits production of moulded Vermiculite parts in the most complicated geometric forms. After pressing the moulded parts feature a very smooth surface and extremely high edge strength and breaking strength.

**Application fields:**

Industrial furnace construction, Petrochemical industry, Steel and Aluminium industry, glass processing, household appliances, oil-, gas- and wood-fired boilers, electrical heaters.

- (1) We are able to supply special formats and special thicknesses on request. We will be pleased to manufacture stampings, milled parts or cuttings according to your drawings.
- (2) The classification temperature is not to be equated with the maximum application temperature, in particular when physical conditions such as tensile or pressure loads are involved. For applications as high-temperature insulation, lower temperatures must always be applied. In these cases, our Engineering department will offer assistance and support.
- (3) Heat transmission calculations for this material can be requested from our Engineering department.

**The information contained in this publication serves only for purposes of clarification, and is not intended to form the basis of contractual obligations.**

Further information and advice on specific details of the products described can be obtained in writing from Techno-Physik Eng. GmbH (Germany). The TechnoPhysik Group is consistently running product development programmes and reserves the right to modify product specifications at any time without notice. The customer/user is thus always obliged to ensure that the material form Techno-Physik Eng. GmbH is suitable for his specific purposes. The specified values are average figures determined from current production and are intended only for information. Warranty claims cannot be derived from these figures. We recommend to test the material for your application.

Sales via any company in the TechnoPhysik Group are subject to the General Terms and Conditions of Sale of the respective company, a copy of which is available on request.